



2294

Notified Body No 2700



Interscience Fire Laboratory

Building 63

Haslar Marine Technology Park

Haslar Road, Gosport

Hampshire PO12 2AG

United Kingdom

Tel. : +44 (0) 20 8692 5050

Fax.: +44 (0) 20 8692 5155

Email: firetesting@intersciencecomms.co.uk

Test Report No: ICL/H17/7967

EN 60332-1-2: 2004

**Tests on electric and optical fibre cables under fire conditions-
Part 1-2 Test for vertical flame propagation for single insulated wire or cable-
Procedure for 1kW pre-mixed flame.**

Sponsored By

Shenzhen Biadi Technology Co.,Ltd
No.8 Lanzhu East Road, Pingshan district
Shenzhen
China

Test Report No: ICL/H17/7967

EN 60332-1-2: 2004

**Tests on electric and optical fibre cables under fire conditions-
Part 1-2 Test for vertical flame propagation for single insulated wire or cable-
Procedure for 1kW pre-mixed flame.**

Sponsored By

Shenzhen Biadi Technology Co.,Ltd
No.8 Lanzhu East Road, Pingshan district
Shenzhen
China

1. Purpose Of Test

To determine the performance of a specimen of a cable when it is subjected to the conditions of test specified in EN 60332-1-2 Tests on electric and optical fibre cables under fire conditions- Part 1-2 Test for vertical flame propagation for single insulated wire or cable- Procedure for 1kW pre-mixed flame and assess the results against the performance requirements given in EN 13501-6 for classification Eca only.

2. Scope Of Test

EN 60332-1-2: 2004 details a method of test for the assessment of the flame propagation characteristics of a single wire or cable. The specimen is deemed to have met the performance requirements of the Standard, if after burning has ceased, the charred or affected portion does not reach within 50mm of the lower edge of the top clamp. In addition, a failure is recorded if charring extends down words to a point greater than 540mm from the lower edge of the top support.

3. Description Of Test Specimen

The description of the specimen given below has been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

The product was a 23AWG 4Pair CAT 6 U/UTP cable having an overall diameter of 6.3mm and consisting of 23AWG solid copper conductors, HDPE insulation, white cross talk, Nylon rip cord and LSZH Violet coloured outer sheath.

There was no marking on the outer sheath of the cable.

The sponsor of the test has supplied a Technical data sheet relating to the cable that was tested and this is given in Annex 1.

The sponsor of the test has stated that the cable is sample from the production run run.

4 Conditioning Of Specimen

The specimen was received on 14th August 2017.

Prior to the test the specimen was conditioned at a temperature of $25 \pm 5^{\circ}\text{C}$ for a minimum period of 16 hours.

5 Date Of Test

The test was performed on 21st August 2017.

6 Test Procedure

The test was performed in accordance with the procedure specified in EN 60332-1-2 and this report should be read in conjunction with that Standard.

The burner was applied for 60 seconds.

7 Test Results

The test results relate only to the behaviour of the specimen of the cable under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimen of the cable in the form in which they were tested. Small differences in the composition or thickness of the cable may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any cable which is supplied or used is fully represented by the specimen which were tested. Uncertainty measurement has not been taken into account when presenting the test results.

Distance between the lower edge of the top support and the onset of charring (mm): 375

Burning extends downwards from the lower edge of the top support (mm): 460

Burning extends downwards from the lower edge of the top support (mm): 85

8 Recommended performance requirement (Annex A : Informative)

The insulated conductor or cable shall pass the test if the distance between the lower edge of the top support and the onset of charring is greater than 50mm.

In addition, a failure shall be recorded if the burning extends downwards to a point greater than 540mm from the lower edge of the top support.

8a. Requirements given in EN 13501-6

The following requirements are given in clause 9.3 for Class Eca

Under conditions of surface flame attack, and with an exposure time in accordance with EN 60332-1-2:2004, Table 1, there shall be no flame spread (*H*) in excess of 425 mm before the test flame extinguishes.

9 Conclusion

The specimen of 23AWG 4Pair CAT 6 U/UTP meets the performance requirement given in Annex A of EN 60332-1-2: 2004 and as the flame spread is <425mm it satisfies the requirements for Classification Eca.

This classification report does not represent type approval or certification of the product. The classification assigned to the construction product in this report is suitable as a declaration of conformity by the manufacturer in the context of System 3 of the certificate of conformity and the CE marking in the framework of the Construction Products Regulation. The inspection body has therefore not cooperated in the selection of samples for the product to be tested, even though the test laboratory provides adequate references from the manufacturer to enable traceability of the tested samples.


This document does not represent type approval or certification of the product.

Prepared by



**C. B. Chong
Fire Scientist**

Approved by



**S. Kumar
Technical Manager**


Date of Issue: 14th September 2017

Annex 1

Product Specification		Biadi Shenzhen Biadi Technology Co.,Ltd	
PART NO.	CAT6-LSZH	ISSUE NO.	A1
DATE OF ISSUE	23rd Nov 2018	PAGE	1 of 1

23AWG 4Pair CAT6 U/UTP Low Smoke Zero Halogen Cable

Construction		
Inner Conductor	Material	Solid Copper
	Diameter, mm	23AWG 0.55±0.01
Insulation	Material	HDPE
	Diameter	1.02±0.02
	Color	Blue & White/Blue Orange & White/Orange Green & White/Green Brown & White/Brown
Crosstalk	Color	White
Rip-Cord	Material	Nylon Rip-Cord
	Color	White
Sheath	Material	LSZH
	Color	Violet
	Other Color	Accept Customized
	Diameter, mm	6.3±0.3
	Sheath Print	23AWG 4PR U/UTP CAT6 LSNH Accept Customized
Packing	Packing length: 100m, 305m, 500m	
	Packing by: Box / Reel	



Specifications on this sheet are subjected to change without prior notice
 Phone: 0086-755-89925302 Fax: 0086-755-89929806
<http://www.biadicable.com> sales01@biadicable.com